



PRODUCT INFORMATION

SIFTRODE BRONZE CUSN

AWS A5.6 E CuSn-A
DIN 1733 E CuSn-7

DESCRIPTION

Basic coated tin bronze electrode for repairing copper and copper tin bronzes, brasses and phosphor bronzes. Suitable for surfacing on brasses, wrought bronzes (CuSn), mild steel and cast steel.

WELDING POSITIONS



Welding current: DC+
Suitable welding positions: PA, PB, PC, PE, PF, PG

TYPICAL WELD METAL COMPOSITION

Mn	0.10 %
Cu	93.00 %
Sn	6.00 %
P	0.20 %

TYPICAL MECHANICAL PROPERTIES

Ult Tensile Strength	≥ 300-350 N/mm2
Redrying	300° / 2h

MATERIAL TO BE WELDED

Base Materials: CUSn2, CUSn6, CUSN8, Copper, Grey cast iron

AVAILABLE FORMATS

ELECTRODE RODS (MMA / SMAW)			
Dia	1.0kg Pkt	5.0kg Pkt	Approx Pcs/KG
3.2mm	RE3003201		31

CURRENT RANGE	
Dia (mm)	Amps
2.5	40-70
3.2	90-140
4.0	140-190

For further information, contact Weldability | Sif technical support on **0870 330 7757** or email service@wholeweld.co.uk



Registered in England No. 1684362
Registered Office: as above

Doc Ref : SIF/PI/RE300