

PRODUCT INFORMATION

SIFAlloy Ti2

AWS A5.16 ER Ti-2

DESCRIPTION

SifAlloy Ti2 is a solid welding wire produced conventionally and then surface cleaned to remove standard metal working lubricants.

WELDING POSITIONS



For use in all positions.

TYPICAL WELD METAL COMPOSITION

Fe	0.20%
C	0.08%
N	0.05
Ti	Bal

TYPICAL MECHANICAL PROPERTIES

Melting Point	1660°C
Ult Tensile Strength	890 N/mm ²
Hardness	57 HV

MATERIAL TO BE WELDED

SifAlloy Ti2 commercial pure Titanium alloy filler metal used for welding alloys of similar composition, has excellent weldability and produces good weld ductility. Also used to fabricate alloy grades where ductility is more important than joint strength.

AVAILABLE FORMATS

WIRE RODS	
Dia	2.5kg
0.9mm	RT920925
1.6mm	RT921625
2.4mm	RT922025

Shielding Gas:	Pure Argon
Current:	DC=+

For further information, contact Weldability | Sif technical support on **0870 330 7757** or email service@weldability-sif.com

Doc Ref : SIF/PSI/RT920925



Registered in England No. 1684362
Registered Office: as above