

# FLUXOFIL 14HD



## Cored Wires C-Mn and low-alloy steels

Fluxofil 14HD is a seamless copper coated rutile flux cored wire with a higher filling degree results in a higher current carrying capacity and high deposition rate. The welding speed is increased which leads to a saving of time and reduction of costs. It can be used in all positions with only one welding parameter setting (24 volts, wire feed = 9m/min, wire dia. 1,2 mm). Fluxofil 14 HD is used for manual welding, as well as in fully mechanized welding by means of the orbital welding unit Citotrack OSG-01 or the vertical welding set Citotrack VSG-01. It is preferably used under mixed shielding gas and is characterized by low spatter loss, good slag removal and finely rippled, pore-free welds without undercut.

Classification	
AWS	A5.20: E71T-1 H4 / E71T-1M H4
EN	758: T 46 2 P C 1 H5 / T 46 2 P M 1 H5

Approvals	Grades
ABS	
BV	
DB	
DNV	
GL	
LRS	
PRS	
RS	
TÜV	
UDT	

see Appendix, Classification Society Approvals, for details pag. 521

### Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	V	N	Cu
0.05	1.20	0.55	-	-	-	-	-	-	-	-	-

### All-weld metal Mechanical Properties

Heat Treatment	Yield Strength N/mm <sup>2</sup>	Tensile Strength N/mm <sup>2</sup>	Elongation A5 (%)	Impact Energy ISO - V (J) - 20 °C	Hardness
As Welded	≥ 460	550-650	≥ 22	≥ 80	-

Gas test: Acc. To EN 439: M21(Arcal 21-Atal 6)

**Shielding Gas:** Acc. To EN 439: M21(Arcal21-Atal6) or C1(Arcal 2)

### Materials

S(P)235-S(P)460, GP240-GP280  
Shipbuilding steels A,B,D,E,AH32 to EH36

### Storage

Keep dry and avoid condensation

### Current condition and welding position

DC+



**Packaging data:** K300 kg. 16

Diameters	1,0	1,2	1,6			