

ER NiCrMo-4 (Alloy C276)

Nickel Alloy TIG/GTAW

Standards

EN/ISO-Standard - 18274

AWS-Standard - A5.14

EN/ISO-Classification - Ni 6276 - NiCr15Mo16Fe6W4

AWS-Classification - ER NiCrMo-4

Features and Applications

- ER-NiCrMo-4 is used for the welding of alloys that have similar chemical compositions, this includes dissimilar materials of nickel-base alloys, steels and stainless steels.
- Due to the high molybdenum content, this alloy offers excellent resistance against stress & corrosion cracking, pitting and crevice corrosion.
- Typically used on pipelines, pressure vessels, chemical processing plants, offshore oil platforms, gas facilities, power generation and marine environments etc.
- Test Certificates can be found online @wilkinsonstar247.com**



Typical Base Materials

N10276, W.Nr: 2.4819, NiMo16Cr15W, Alloy C4, Alloy C276*

* Illustrative, not exhaustive list

Welding Positions

EN ISO 6947 - PA, PB, PC, PD, PE, PF, PG

Shielding Gases

EN ISO 14175 - TIG: I1 (Argon)

Polarity

TIG DC (-)

Mechanical Properties

Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation (%)	Impact Strength (J)
≥690	-	-	-

Mechanical properties are approximate and may vary based on the heat, shielding gas, welding parameters and other factors.

Chemical Composition of Weld Metal %

C %	Mn %	Fe %	P %	S %	Si %	Cu %	Ni %	Co %	Cr %	Mo %	V %	W %
max	max	4.00	max	max	max	max	50.00	max	14.50	15.00	max	3.00
0.020	1.00	7.00	0.020	0.015	0.08	0.50	min	2.50	16.50	17.00	0.30	4.50

Packaging Data

Part No.	Diameter Ø (mm)	Package Length (mm)	Package Weight (Kg)	Package Type
6011100596	1.60	1000	5	Cardboard Tube
6011100597	2.40	1000	5	Cardboard Tube
6011100598	3.20	1000	5	Cardboard Tube

Liability: Whilst all reasonable efforts have been made to ensure the accuracy of the information contained, this information is subject to change without notice and can be only considered as suitable for general guidance.

