

CF2 - G3Si1 (Endurance Pac)

Mild Steel MIG/GMAW

Standards

EN/ISO-Standard - 14341-A

AWS-Standard - A5.18

EN/ISO-Classification - G 42 3 C1 / G 42 4 M21 3Si1

AWS-Classification - ER 70S-6

Features and Applications

- Bulk wire drum system that offers a high productivity solution for continuous high volume welding applications.
- A non-copper coated solid wire suitable for single pass or multipass welding of unalloyed and low-alloyed carbon-manganese steels.
- Environmentally friendly when compared against traditional copper wires offering less fume and smoke in the working environment.
- Advantages of a stable arc when working with increased welding speeds that achieves high quality welds with almost no spatter.
- Good mechanical properties at sub-zero temperatures down to -40°C.
- Typically used on boilers, industrial machinery, bridges, shipbuilding, automotive, rail, structural and engineering fabrications etc.
- Green wire is produced using virgin raw materials sourced from specialised steel mills, which ensures consistent reliability and quality.
- **Test Certificates can be found online @wilkinsonstar247.com**



Wire Length	0.80	1.00	1.20
Meters	68,375	43,062	29,625
Miles	42.50	26.76	18.41

Typical Base Materials

S185, S235, S275, S355 - Grade A, B, D, AH32 to DH36 - L210, L240, L290, L360, L240NB, L290NB, L360NB, L360QB, L240MB, L290MB, L360MB, L415MB - X42, X46, X52, X60 - P235T1, P235T2, P275T1 - P275T2, P355N - P235GH, P265GH, P295GH, P355GH - S275, S355, S420, S275M, S275ML, S355M, S355ML, S420M, S420ML*

* Illustrative, not exhaustive list

Welding Positions

EN ISO 6947 - PA, PB, PC, PD, PE, PF, PG

Shielding Gases

EN ISO 14175 - C1, M21

Polarity

MAG DC (+)

Chemical Composition % (Typical)

C %	Si %	Mn %	P %	S %	Cu %	Cr %	Ni %	Mo %	Al %	V %	Zr+Ti %
0.07	0.85	1.45	<0.025	<0.025	0.010	<0.15	<0.15	<0.15	<0.020	<0.030	<0.15

Packaging Data

Part No.	Diameter Ø (mm)	Package Weight (Kg)	Package Type	Pallet Quantity
3010200918	0.80	250	Drum	4
3010200922	1.00	250	Drum	4
3010200926	1.20	250	Drum	4

BS300 spools also available.



Welding Parameters

Ø mm	0.80	1.00	1.20
Current (A)	60-180	80-230	120-350
Voltage (V)	18-22	20-28	26-34

Mechanical Properties (Typical) - C1

Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation (%)	Impact Strength (J)	Test Temperature
540	440	30	70	-30°C

Mechanical Properties (Typical) - M21

Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation (%)	Impact Strength (J)	Test Temperature
580	460	26	90	-40°C

Mechanical properties are approximate and may vary based on the heat, shielding gas, welding parameters and other factors.

Liability: Whilst all reasonable efforts have been made to ensure the accuracy of the information contained, this information is subject to change without notice and can be only considered as suitable for general guidance.



Exclusive Partnership



TDS.CF2.DRUM.GMAW_rev1